

TECHNICAL DATA SHEET

Issue: 2

Version: 4

BK-IN KUL, BK-IN KUL BRILIANT**RZ-TLP-024****Date: 3.9.2019.****1. PRODUCT AND COMPANY INFORMATION**

Commercial product name: BK-IN Kul
BK-IN Kul Brilliant

Manufacturer:

Banja Komerc Bekament DOO
34304 Banja
Arandelovac
tel. 034-6777-500
fax. 034-6777-505
e-mail: komercijala@bekament.com

TDS contact: email: laboratorija@bekament.com

2. DESCRIPTION, FIELD OF APPLICATION

BK-IN Kul is a decorative mosaic high-quality emulsion acrylic based plaster. It is also produced using a multicolor marble grain. It is intended for the decoration and protection of interior wall surfaces. It may be used for exterior use. However, due to its particularly fine grains and very light shades it is recommended for interior use. It is characterized by solid adhesion to the surface, exquisite workability, high level of hardness, and waterproof abilities.

BK-IN Kul Brilliant also contains mineral shiny shavings, thus particularly pointing out the decorative effect of this material.

BK-IN Kul/BK-IN Kul Brilliant is not recommended for use on horizontal surfaces which are exposed to the direct effects of stagnant water.

Grain size: 1 mm

3. COMPOSITION

Chemical composition: Aqueous polymer emulsion, water, additives, multi-color marble grains.

Hazardous substances: In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, this product is not classified as a hazardous product.

4. TECHNICAL CHARACTERISTICS

Density, g/dm ³ (EN ISO 2811-1)	1,500-1,700
Adhesion, MPa (EN 1542)	> 0,3 MPa according to EN 15824
Water absorption, kg/(m ² h ^{0,5}) (EN 1062-3)	0.1-0.5 (Class W2 according to EN 15824)
Vapor permeability, g/(m ² d) (EN ISO 7783-2)	> 150 (Class V1 according to EN 15824)
Diffuse resistance coefficient-μ (EN ISO 7783-2)	> 20

RZ-TLP-024Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET	Issue: 2	Version: 4
BK-IN KUL, BK-IN KUL BRILIANT	RZ-TLP-024	Date: 3.9.2019.

Heat conductivity- $\lambda_{10, dry}$, W/(m.K) (EN 1745 Table A.12)	0.35
Indicative consumption, kg/m ²	~3
Packaging, kg	25;

5. OTHER CHARACTERISTICS

Physical appearance: Pasty mass in combination with multi-color grains

Odor: Specific of polymeric binders

pH value (EN ISO 787-9): 8-10

Dry matter content (EN ISO 3251), %: ~85

VOC* content, g/l: < 10 (maximum value allowed A (a) 30 g/l)

*VOC: Volatile Organic Compound;

BK-IN Kul is made in 5 natural colors, while BK-IN Kul Briliant is made in 3 colors. Other combinations on the base of colored grains may be made at the request of customers.

6. SURFACE PREPARATION

The surface to which the plaster is applied must be firm, clean, and dry, without poorly bound parts, greasy stains, etc. Lime, cement, and cement-lime mortars (at least one month old), fiber-cement and gypsum-cardboard panels, surfaces processed using cement adhesives (at least 7 days old), concrete surfaces (at least one months old), etc. are all appropriate surfaces. The product is not suitable for use on mortars where gypsum has just been applied, nor is it suitable for use on wet surfaces. Before applying, the surface must be coated using BK-Acryl primer, while in the case of darker surfaces, BK-MicroGrund Universal must be used. The drying time of primer before applying plaster is at least 12 hours.

Much care should be given to preparing the surface because any irregularities in the form of uneven surfaces make any corrections of the plaster more difficult. Old patched up surfaces must be leveled out using a new layer of adhesive before installing the decorative plaster. The surfaces must also be evened out before applying the decorative plaster. Applications on patched surfaces which contain materials of different absorption characteristics gives as the final result an uneven layer of the decorative plaster when it comes to the issue of shade/color of the rock.

7. PREPARATION AND APPLICATION

Before use, the plaster must be stirred well. As needed, dilute using a small amount of water up to 1 % (up to 250 ml/25 kg) with the objective of adjusting the plaster consistency until the mass becomes foamy. Mixing the plaster must be done by pouring it from one bucket into the other, by hand, or using a slow-rotating electric blender. Mixing the material using a standard fast-rotating electric blender may lead to damages of the colored marble grains and thus to turbidity and discoloration of the emulsion.

The plaster is applied manually using a stainless metal trowel in the 1.5-2.0 mm width in the upward direction. Smooth out the material using the same tools in one direction immediately after application. The layer must be even, evenly thick and without empty spaces between grains. While smoothing out the surface, the tools must periodically be cleaned and excess emulsion must be removed in order to avoid the mass from becoming

TECHNICAL DATA SHEET	Issue: 2	Version: 4
BK-IN KUL, BK-IN KUL BRILIANT	RZ-TLP-024	Date: 3.9.2019.

murky after drying. The murkiness is manifested in the form of milky white stains on the surface of the mortar.

Work must be even and without interruptions in continuous wall surfaces so as to avoid any irregularities created due to the adhesion of surfaces, irregular drying, etc.

Air and surface temperature during installation should be in the +5 °C to +30 °C range. Do not work under direct sunlight, wind, or rain. After 6 h of drying under normal conditions (T = + 23-25 °C, 50-60% r.v.v.) the mortar is dry to the touch. Resistance to precipitation is achieved after 24 hours of drying under normal conditions. High moisture and low temperatures may significantly lengthen the time it takes for the plaster to bind.

8. MAINTENANCE

BK-IN Kul, BK-IN Kul Brilliant plasters do not require any particular maintenance. It is recommended that the surface is occasionally dusted off. Any possible impurities may be removed using warm water and a universal house cleaning supply (laundry detergent/dish soap). After that, rinse using a stream of water. No cleaning or washing using abrasive products or tools is permitted.

9. CLEANING THE TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically. Removal may be easier if the tools are submerged in water over a period of several hours.

10. HANDLING AND STORAGE

No special caution during use is needed when using the product properly. Keep out of reach of children.

Store at temperatures between +5 ° C and +25 ° C, protected from direct sunlight and frost.

Shelf life: 18 months.

11. PERSONAL PROTECTION

Respiratory tract protection: Not needed when the rooms are well aerated.

Hands and body protection: When the skin is repeatedly exposed to the mass, a preventative use of protection gloves is recommended. Use long-sleeve work overalls.

Eye protection: Use safety goggles as a preventative measure.

12. ECOTOXICOLOGICAL INFORMATION

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into sewage and waterways.

13. STORAGE

In accordance with local/regional/European/national regulations.

14. OTHER INFORMATION

RZ-TLP-024

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET

Issue: 2

Version: 4

BK-IN KUL, BK-IN KUL BRILIANT**RZ-TLP-024****Date: 3.9.2019.**

Certain deviations of the mortar shade in relation to the appropriate shade in the color chart are possible due to the use of natural and colored grains. The uneven character of color shading of mortar installed may be the consequence of inappropriate conditions at installation, less time spent on making the surface uniform, differences in absorption, and the roughness of the base.

All plaster for a single object must be ordered at one time. Banja Komerc Bekament DOO does not guarantee a complete match of shades of plasters from various batches. Deviations in terms of tone are not subject to claims.

If the contractor notices an aesthetic or application deficiency while using the plaster, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer regarding the aesthetic characteristics upon using a significant portion or the entire amount of the materials are not subject to claims.

15. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is assumed that the contractor has mastered the techniques of installing and use of various products.

Matters written herein bind us in no way.

This document replaces all previous versions. All previous versions, starting with the listed date the document was compiled, are void.

Date: 06.02.2013.

Previous version: 2.3. – 15.11.2018.

Amended chapters: 6