

TECHNICAL DATA SHEET	Edition:2	Version:2
SiproFix BK-110	RZ-TLP-015-02	Date: 28.08.2020.
Prepared by: Ana Blagojevic	Approved by: Biljana Kamaljević	

1. IDENTIFICATION OF THE PRODUCT AND THE COMPANY

Trade name of the product: SiproFix BK-110

Details about the manufacturer:

Banja Komerc Bekament DOO

34304 Banja

Arandelovac

tel. 034-6777-500

fax. 034-6777-505

e-mail: komercijala@bekament.com

Contact for TDS preparation:

e-mail: laboratorija@bekament.com

2. DESCRIPTION AND SCOPE

For laying ceramics on wall, floor and facade surfaces, exclusively on solid substrates (concrete, cement and lime-based mortars), for exterior and interior use. It is used for laying absorbent and poorly absorbent ceramic tiles dimensions up to 60x60cm. Suitable for use in bathrooms, kitchens, balconies and terraces. Can be used in a system with BK-HydroStop 1 waterproofing coating.

SiproFix BK-110 is classified in group C1T , according to EN 12004.

3. COMPOSITION

Chemical composition: Grey Portland cement, polymer binder, additives, mineral filler.

Hazardous substances: In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard

4. TECHNICAL CHARACTERISTICS

Bulk density, g/dm³	1100-1300
Adhesion hardness, MPa (EN 1348)	
inital	≥ 0,5 (according EN 12004)
after standing in water	≥ 0,5 (according EN 12004)
after temperature aging	≥ 0,5 (according EN 12004)
after a freeze-thraw cycle	≥ 0,5 (according EN 12004)
Adhesion hardness after 20 min MPa, open time, (EN 12004)	≥ 0,5

RZ-TLP-015-02

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET	Edition:1	Version:0
SiproFix BK-110	RZ-TLP-015-02	Date: 24.01.2020.

Indecative consumption, kg/m²	~3-5 depending on the substrate thickness and application
Sliping, mm (EN 1308)	< 0,5
Packaging, kg	25; 5

5. OTHER CHARACTERISTICS

Appearance: Grey powder

Wet adhesive pH value: 11-13

6. SUBSTRATE

The surface to which the adhesive is applied must be firm, clean, and dry, without poorly bound parts, greasy stains, etc. The following surfaces are appropriate: cement-lime mortars (at least one month old), concrete surfaces (at least three months old), gypsum-cardboard panels, fiber-cement panels, etc. Filling in the cracks 5-6 mm can be done with adhesive 24h before laying the tiles. Filling in larger cracks and leveling out in greater thickness must be done using mortar BK-Mal 220 mortar, not adhesive. Before laying the tiles it is recommended to coat with BK-Ultra Prime substrate, dulited according the instruction, in order to improve the adhesion. When it comes to old and uneven absorbing substrates, as well as when it comes to porous highly absorbent surfaces, it is necessary to coat the substrate with dulited BK-Bond, min. 4h before laying the tiles. In case of laying tiles on surfaces infected with wall mold, it is necessary to disinfect with BK-Sanicide.

7. PREPARATION AND APPLICATION

Preparation of the mass is performed by lightly adding the powder into about 25-27 % of water (approx. 6.5 l of water to 25 kg powder), with intensive stirring using an electric blender until the mass becomes fully homogenized. The mass must be left to set for at least 10 minutes. After that, stir yet again and, if needed, add water in order to set the appropriate adhesive consistency.

The adhesive is applied using a notched trowel onto the surface. The usual length of teeth is 4 to 6mm when attaching normal ceramic tiles 10-25 cm in size. Tools with larger teeth are used for attaching larger tiles. When laying mosaic and smaller tiles, smaller tools with shorter teeth must be used. Press the tiles into the layer of adhesive on the substrate. When applying the adhesive, make sure that at least 65% of the surface of the tile is covered with adhesive if used in the interior, and at least 90% if used in the exterior. In the case of laying tiles on loaded surfaces, as well as in the case of laying tiles of larger formats, apply the adhesive with a notched trowel on the back of the tile, which creates a contact surface between the adhesive and the tile of min. 90%. Open time of the adhesive applied under normal conditions (T=+23-25 °C, relative humidity=50-60%) is at least 30 minutes, so the surface to which the adhesive is applied during installation must be planned accordingly. Tiles should be laid while the adhesive is fresh (before crust formation). The stated open time is considerably

RZ-TLP-015-02

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET

Edition:1

Version:0

SiproFix BK-110**RZ-TLP-015-02****Date: 24.01.2020.**

shortened in the conditions of higher temperatures, absorbent surfaces, wind, etc. When working with highly absorbent tiles, they must be previously soaked in water. The prepared adhesion mass is good for use up to 2 hours, depending on conditions at installation. Air and surface temperature during installation should be in the +5 °C to +25 °C range. High moisture and low temperatures may lengthen the drying time. Under normal conditions it takes 24 hours of drying for the surface to be able to support light walking and grouting. Under normal conditions it takes 7 days of drying for the surface to be fully functional.

8. CLEANING OF TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically

9. HANDLING AND STORAGE


The material must be transported in sealed bags. If the product is used in closed rooms, make sure the space is well ventilated. Protect your eyes and skin when working with wet adhesive due to an alkaline reaction. Keep out of reach of children. Store the material in dry rooms, on pallets, protected from moisture. Shelf life: 12 months.

10. PERSONAL PROTECTION

Respiratory tract protection: In case the process causes excessive dust, use a face mask. Hands and body protection: Use safety gloves. Wash hands using water each time the work is interrupted. Use long-sleeve work overalls. Eye protection: Use safety goggles in order to protect the eyes from the dust and wet adhesive.

11. REGULATION INFORMATION

In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard



Hazard

Skin irritation, Category 2: H315
Skin sensitization, category 1: H317
Heavy eye damage, Category 1: H318

RZ-TLP-015-02Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET	Edition:1	Version:0
SiproFix BK-110	RZ-TLP-015-02	Date: 24.01.2020.

Specific target organ toxicity - single exposure, respiratory tract irritation, category 3: H335

H-labels:

H315 Causes skin irritation.

H317 May cause an allergic skin reaction.

H318 Causes serious eye damage.

H335 May cause respiratory irritation

P-labels:

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352 IF ON SKIN: Wash with plenty of water.

P333+P313 If skin irritation or rash occurs: Seek medical advice/opinion.

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P304+P340 IF INHALED: Remove person to fresh air and keep comfortable for breathing.

12. ECOTOXICOLOGICAL INFORMATION

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into waterways because an alkaline reaction may occur.

13. DISPOSAL METHOD

In accordance with local/regional/European/national regulations.

14. OTHER INFORMATION

If the contractor notices an aesthetic or application deficiency while using the adhesive, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer upon using a significant portion or the entire amount of the materials are not subject to claims.

15. NAPOMENA

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty. Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is assumed that the contractor has mastered the techniques of installing and use of various products. Matters written herein bind us in no way.

RZ-TLP-015-02

Banja Komerc Bekament d.o.o., Banja / 34304 Arandelovac | www.bekament.com

TECHNICAL DATA SHEET

Edition:1

Version:0

SiproFix BK-110**RZ-TLP-015-02****Date: 24.01.2020.**

This document supersedes all previous versions, which are considered invalid from the specified date.

Date: 24.01.2020.

Previous version: 2.1-24.01.2020.

Amended chapters: 2.