

TECHNICAL DATA SHEET	Issue: 1	Version: 3
BK-HIDROSTOP BASE	RZ-TLP-016-03	Date: 11.05.2022.

1. PRODUCT AND COMPANY INFORMATION

Commercial product name:

BK-HidroStop Base

Manufacturer:

Banja Komerc Bekament DOO
 Kralja Petra Prvog 132, 34304 Banja
 Arandelovac
 tel. 034-6777-500
 fax. 034-6777-505
 email: komercijala@bekament.com

TDS contact:

email: laboratorija@bekament.com

2. DESCRIPTION, FIELD OF APPLICATION

BK-HidroStop Base is a one-component, polymer-cement-based, waterproof coat. It is intended for both horizontal and vertical insulation of potentially damp areas (kitchens, bathrooms, swimming pools, basements, balconies, etc.). It is flexible and is characterized by good adhesion onto different surfaces, such as concrete, cement mortars, bricks, etc. It is intended for both internal and external use, for both positive and negative water pressure ≤1,5 bar. The material is not intended for final surface processing, nor is it intended for permanent submersion into water without an appropriate final coating. The product is classified as a CM P according to the EN 14891 standard.

3. COMPOSITION

Chemical composition: Grey Portland cement, polymer binder, additives, mineral fillers.

Hazardous substances: In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard

4. TECHNICAL CHARACTERISTICS

Bulk density, g/dm³	1,100-1250
Adhesion, MPa (EN 14891)	
♣ normal conditioning	≥ 0.5 according to EN 14891
♣ after water conditioning	≥ 0.5 according to EN 14891
♣ after temperature aging	≥ 0.5 according to EN 14891
♣ after a freeze-thaw cycle	≥ 0.5 according to EN 14891

TECHNICAL DATA SHEET	Issue: 1	Version: 3
BK-HIDROSTOP BASE	RZ-TLP-016-03	Date: 11.05.2022.

Adhesion after contact with a chlorinated base, MPa (EN 14891)	≥ 0.5 according to EN 14891
Flexural strength after 28 d, MPa (EN 1015-11)	≥ 2,0

Compressive strength after 28 d, MPa (EN 1015-11)	≥ 6,0 Class CS IV according to EN 998-1
Hardened plaster density, g/dm³ (EN 1015-10)	1300-1400
Water resistance (EN 14891, EN 206-1 / HA)	≥ 0.5 according to EN 14891 (waterproof at 168 h at 150 kPa)
EN 1504-2	
Adhesion, N/mm² (EN 1542)	≥ 0,8 (0,5)
Vapor permeability, m (EN 7783)	s _D < 5 m, class I
Capillary absorption of water, kg/(m²h^{0,5}) (EN 1062-3)	< 0,1
Indicative consumption, kg/m²	~1,20 depending of surface quality
Packaging, kg	20;

5. OTHER CHARACTERISTICS

Physical appearance: Grey powder

Wet plaster pH value: 11-13

6. SURFACE PREPARATION

The surface to which the product is applied must be firm, clean, and dry, without poorly bound parts, greasy stains, etc. The following surfaces are appropriate: cement-lime mortars (at least one month old), concrete surfaces (at least three months old), fibercement and gypsum-cardboard panels, brick walls, bricks, etc.

Before applying the waterproofing, it is recommended to use the BK-Ultra Prime on the surface.

In the case of old and unevenly absorbing substrates, as well as in the case of porous highly absorbent substrates, it is necessary to coat with BK-Ultra Prime, min. 4h before applying waterproofing.

In the case of surfaces that peel, wear and / or dust, it is necessary to remove all loose bonds and then impregnate the substrate with BK-Penetrat. It is necessary to wash the concrete surfaces well with hot water in order to remove the present impurities and then coat them with BK-Beton Kontakt.

TECHNICAL DATA SHEET	Issue: 1	Version: 3
BK-HIDROSTOP BASE	RZ-TLP-016-03	Date: 11.05.2022.

In the case of coating surfaces infected with wall mold, it is necessary to disinfect with BK-Sanacid.

7. PREPARATION AND APPLICATION

Preparation of the mass is performed by lightly adding the powder into about 26 % of water (-6,5 l of water to 25 kg of powder), with constant stirring using an electric blender until the mass becomes fully homogenized. The mass must be left to set for 5 minutes. After that, re-stir and apply onto the previously prepared surface within 60 minutes. Application is done using a brush, in two coatings, using the crisscross method. A third layer may be applied if needed. Individual layer thickness is around 1 mm. The next layer must be applied after the previous one has solidified. The total thickness of the spread must be at least 2 mm. All intermissions and extensions in the concrete, etc. must be filled using the appropriate sealing material. Sealing must not be done using a hydro-insulation coat. Hydro-insulation sealing tape must be used in the corners in order to achieve quality hydro-insulation. Furthermore, performances of the hydro-insulation coat may be further improved by pressing a reinforced polyester canvas into the first layer of the coat. Waterproofing coat should be protected from drying too quickly.

The prepared mass must be used within 2 hours.

Air and surface temperature during installation should be in the +5 °C to +30 °C range. Do not work under direct sunlight, wind, or rain. After 24 hours of drying under normal conditions (T = + 23-25 °C, 50-60% r.v.v.), it is desirable to continue laying the tiles because during the long drying of the waterproofing coating, the absorbency of the substrate is significantly reduced.

8. CLEANING THE TOOLS

All tools must be thoroughly washed using water immediately after use. If the tools are not washed immediately after use, remove the hardened residue mechanically.

9. HANDLING AND STORAGE

The material must be transported in sealed bags. If the product is used in closed rooms, make sure the space is well ventilated. Protect your eyes and skin when working with wet mortar due to an alkaline reaction. Keep out of reach of children.

Store the material in dry rooms, on pallets, protected from moisture.

Shelf life: 12 months.

10. PERSONAL PROTECTION

Respiratory tract protection: In case the process causes excessive dust, use a face mask.
Hands and body protection: Use safety gloves. Wash hands using water each time the work is interrupted. Use long-sleeve work overalls.

Eye protection: Use safety goggles in order to protect the eyes from the dust and wet mortar.

11. REGULATION INFORMATION

In accordance with the (EC) Regulation No. 1272/2008 on classification, labelling and packaging of substances and mixtures, through which the CLP/GHS classification and labeling system was introduced into law, grey Portland cement is a hazardous substance. The product is therefore classified a hazardous one with the following label: Hazard



Hazard

Skin irritation, Category 2 H315

Eye damage, Category 1 H317

Severe eye damage, category 1: H318

Specific target organ toxicity -single exposure, respiratory tract irritation, category 3: H335

H-labels:

H315 Causes skin irritation.

H317 May cause an allergic skin reaction.

H318 Causes serious eye damage.

H335 May cause respiratory irritation.

P-labels:

P280 Wear protective gloves/protective clothing/eye protection/face protection.

P302+P352 IF ON SKIN: Wash with plenty of water.

P333+P313 If skin irritation or rash occurs: Get medical advice/attention.

P305+P351+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P304+P340 IF INHALED: Remove person to fresh air and keep comfortable for breathing.

12. ECOTOXICOLOGICAL INFORMATION

Based on experiences and information currently available, no negative health effects are known when the product is used appropriately. Prevent uncontrolled discharge into waterways because an alkaline reaction may occur.

13. STORAGE

In accordance with local/regional/European/national regulations.

14. OTHER INFORMATION

TECHNICAL DATA SHEET	Issue: 1	Version: 3
BK-HIDROSTOP BASE	RZ-TLP-016-03	Date: 11.05.2022.

If the contractor notices an aesthetic or application deficiency while using the mortar, he is obliged to cease the works and notify the manufacturer of this. The manufacturer will consider the claim in the shortest possible time frame. Complaints to the manufacturer upon using a significant portion or the entire amount of the materials are not subject to claims.

15. NOTE

Banja Komerc Bekament DOO performs product quality checks using its own laboratories. It also regularly tests its products in certified laboratories. The Data Sheet is the product of our knowledge and previous practical experience. The purpose of the Data Sheet is to serve as a recommendation in order to achieve the best possible results. If weather and other conditions are different than those described in our instructions, our instructions need to be taken as general guidelines, without an installation warranty.

Banja Komerc Bekament DOO assumes no liability for damages resulting from the improper use or incorrect product selection, as well as for poorly executed work. It is assumed that the contractor has mastered the techniques of installing and use of various products.

Matters written herein bind us in no way.

This document supersedes all previous versions, which are considered invalid from the specified date.

Date: 11.05.2022.

Previous version: 1.2 - 24.12.2021.

Amendments: Chapters: 4